

LUMINA

| | | | |
|--|---------------|---|--|
| SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE | | 100% POLIESTER 100% POLYESTER 100% POLIESTERSKO VLAKNO 100% POLYESTER 100% POLIESTERE | |
| ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA | 140 cm +/- 2% | TEŽA WEIGHT TEŽINA GEWICHT PESO | LUMINA plain 460 gr/m2 +/-5% LUMINA damask 460 gr/m2 +/-5% LUMINA diamond 370 gr/m2 +/-5% LUMINA stripe 370 gr/m2 +/-5% |

| TEST | STANDARD | REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI | |
|--|---|--|---------------------------------------|
| | | OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO | VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA |
| RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE | EN ISO 13934-1 | 1579 N (39,3%) | 1565 N (42,1%) |
| RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE | EN ISO 13937-3 | 53.7 N | 56.2 N |
| DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA | prEN ISO 13936-2 PRI/AT/KOD/BEI 180 N | 2.5 mm | 2,5 mm |
| OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE | DIN EN ISO 12947-1 DIN EN ISO 12947-2 | >100.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI | |
| PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING | EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI | 5 | |
| OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT SOLIDITA DEL COLORE ALLA LUCE | EN ISO 105-B02 | >5 | |
| OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT SOLIDITA DEL COLORE ALL'ABRASIONE | EN ISO 105-X12 | SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO | MOKRO/WET/ MOKRO/NASS/ UMIDO |
| VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI AZO COLORANTI | DIN EN 14362/1.3 | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR IMPERCETTIBILE | |
| VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTNO DI COLORANTI ALLERGENICI | | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR IMPERCETTIBILE | |

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si



| | | |
|--|------------------------------------|--|
| TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO | BS 5852 SOURCE 0 EN 1021 part 1 | PRESTAL PASSED PROŠAO UEBERSTANDEN PASSATO |
|--|------------------------------------|--|

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGLICH
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si