

## BEATRICE QC

|   |  |  |                                   |
|---|--|--|-----------------------------------|
| SESTAVA TKANINE<br>COMPOSITION<br>SIROVINSKI SASTAV TKANINE<br>ZUSAMMENSETZUNG<br>COMPOSIZIONE TESSUTO  |  | 60% POLIESTER, 40% POLIPROPILEN<br>60% POLYESTER, 40% POLYPROPYLENE<br>60% POLIESTER, 40% POLIPROPILEN<br>60% POLYESTER, 40% POLYPROPYLEN<br>60% POLIESTERE, 40% POLIPROPILENICA |                                   |
| ŠIRINA<br>WIDTH<br>ŠIRINA<br>BREITE<br>ALTEZZA  | 140 cm +/-2%   | TEŽA<br>WEIGHT<br>TEŽINA<br>GEWICHT<br>PESO  | 307 gr/m <sup>2</sup> +/-5%       |
| TEST  | STANDARD   | REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI  |                                   |
|   |  | OSNOVA/WARP/<br>OSNOVA/KETTE/ORDITO  | VOTEK/WEFT/<br>POTKA/SCHUSS/TRAMA |
| RAZTEZNA TRDNOST<br>TENSILE STRENGTH<br>ČVRSTOČA NA RASTEZANJE<br>ZUGFESTIGKEIT<br>RESISTENZA ALLA TRAZIONE   | EN ISO 13934-1   | 1100 N   | 1400 N                            |
| RAZTRŽNA TRDNOST<br>TEAR STRENGTH<br>ČVRSTOČA NA KIDANJE<br>WEITERREISSFESTIGKEIT<br>RESISTENZA ALLA LACERAZIONE  | EN ISO 13937-3   | 190 N  | 130 N                             |
| DRSNOST NITI<br>RESISTANCE TO SEAM SLIPPAGE<br>OTPORNOST NA POMJERANJE /POMERANJE ŠAVA<br>NAHTSCHIEBEWIDERSTAND<br>RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA | EN ISO 13936-2   | 6 mm   | 5 mm                              |
| OBSTOJNOST TKANINE NA DRGNJENJE<br>ABRASION RESISTANCE<br>POSTOJANOST TKANINE NA TRLJANJE<br>SCHEUERBESTÄNDIGKEIT<br>RESISTENZA ALL'ABRASIONE                 | EN ISO 12947-1<br>EN ISO 12947-2   | 100.000<br>OBRATOV/REVS./OBRTAJA /TOUREN/GIRI  |                                   |
| PILING<br>PILLING RESISTANCE<br>PILING<br>PILLBILDUNG<br>RESISTENZA PILLING   | EN ISO 12945-2<br>2.000 OBRATOV/<br>REVS./OBRTAJA<br>/SCHEUERTOUR<br>EN/GIRI | 4  |                                   |
| OBSTOJNOST BARVE NA SVETLOBO<br>COLOUR FASTNESS TO LIGHT<br>POSTOJANOST BOJE NA SVJETLO/SVETLOST<br>LICHTECHTHEIT<br>RESISTENZA ALLA LUCE                     | EN ISO 105-B02<br>Method 2   | 4  |                                   |
| OBSTOJNOST BARVE NA DRGNJENJE<br>COLOUR FASTNESS TO RUBBING<br>POSTOJANOST BOJE NA TRLJANJE<br>REIBECHTHEIT<br>RESISTENZA COLORE ALL'ABRASIONE                | EN ISO 105-X12   | SUHO/DRY/SUHO/<br>SUVO/TROCKEN/SECCO   | MOKRO/WET/<br>MOKRO/NASS/UMIDO    |
|   |  | 4-5  | 4-5                               |
| TEST NEGORLJIVOSTI<br>FIRE RETARDANT<br>TEST NEGORIVOSTI<br>BRENNVERHALTEN<br>IGNIFUGO  | BS5852<br>Source 0   | PRESTAL<br>PASSED<br>PROŠAO<br>BESTANDEN<br>SUPERATO   |                                   |
| OEKO-TEX  |  | DA<br>YES<br>DA<br>JA<br>SI  |                                   |
| ZAŠČITA TKANINE:<br>FABRIC PROTECTION:<br>ZAŠTITA TKANINE:<br>STOFFSCHUTZ:<br>PROTEZIONE TESSUTO:   |  | QUICK CLEAN  |                                   |

MED BARVNIMI PARTIJAMI SO MOŽNA Odstopanja v barvi.  
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE.  
MOGUČA SU Odstupanja u boji kod proizvodnje.  
FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH.  
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

