

## CHENILLE

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE		88% POLIESTER, 12 % NYLON / 95 % POLIESTER, 5 % BOMBAŽ 88% POLYESTER, 12 % NYLON / 95 % POLYESTER, 5 % COTTON 88% POLIESTERSKO VLAKNO, 12 % NYLON / 95 % POLIESTRSKO VLAKNO, 5 % PAMUK	
ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		88% POLYESTER, 12 % NYLON / 95 % POLYESTER, 5 % BAUMWOLLE 88% POLIESTERE, 12% NYLON / 95% POLIESTERE, 5% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	145 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	300 gr/m <sup>2</sup> +/-5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1134 N (37,6%)	959 N (23,4%)
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	115,3 N	55,7 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2,8 mm	2,8 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-1 EN ISO 12947-2	64.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OB RTAJA /SCHEUERTOUREN/G IRI	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02 Method 2	3 - 4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		5	5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB B 82.02- 2,3,4,9	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	

ZAŠČITA TKANINE:  
FABRIC PROTECTION:  
ZAŠTITA TKANINE:  
STOFFSCHUTZ:  
PROTEZIONE TESSUTO:

VODOODBOJNI NANOS  
WATER REPELLENT  
VODOODBOJNI NANOS  
WASSERABWEISEND  
IDROPELENTE

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI  
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE  
MOGUĆA SU ODSSTOPANJA U BOJI KOD PROIZVODNJE  
FARBNIANSEN SIND MOEGELICH  
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

