

## LONDON

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		100% POLIESTER 100% POLYESTER 100% POLIESTERSKO VLAKNO 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	350 gr/m <sup>2</sup>


TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/OR DITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2227 N (49,2%)	2025 N (46,0%)
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	193,1 N	155,7 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	3,5 mm	4,5 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-1 EN ISO 12947-2	>100.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRATAJA /SCHEUERTOUREN/GIRI	4 - 5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02 Method 2	4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		4-5	5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB B 82.02-2,3,4,9	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

<b>VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE</b> <b>ALERGY CAUSING DYES</b> <b>SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE</b> <b>ALLERGISIERENDE FARBSTOFFE</b> <b>CONTENUTO DI COLORANTI ALLERGENICI</b>		<b>NI ZAZNANA</b> <b>NOT DETECTABLE</b> <b>NE SADRŽI</b> <b>NICHT NACHWEISBAR</b> <b>NON RILEVABILE</b>
<b>TEST NEGORLJIVOSTI</b> <b>FIRE RETARDANT</b> <b>TEST NEGORIVOSTI</b> <b>BRENNVERHALTEN</b> <b>IGNIFUGO</b>	<b>BS 5852 Source 0</b>	<b>PRESTAL</b> <b>PASSED</b> <b>PROŠAO</b> <b>UEBERSTANDEN</b> <b>SUPERATO</b>

**MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI**  
**COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE**  
**MOGUČA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE**  
**FARBNIANSEN SIND MOEGLICH**  
**TRA I VARI LOTTI POSSONO VERIFICARCI DELLE VARIAZIONI NEL COLORE.**



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631  
 Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si