

ORION

| | | | |
|--|------------|---|--------------|
| SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE | | 57% POLIESTER, 43% AKRIL 57% POLYESTER, 43% ACRYLIC 57% POLIESTERSKO VLAKNO, 47% AKRILNO VLAKNO 57% POLYESTER, 43% ACRYL 57% POLIESTERE, 43% ACRILICA | |
| ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA | 140 cm ±2% | TEŽA WEIGHT TEŽINA GEWICHT PESO | 341gr/m2 ±5% |

| TEST | STANDARD | REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI | |
|---|---|--|---------------------------------------|
| | | OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO | VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA |
| RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE | EN ISO 13934-1 | 1517 N | 1168 N |
| RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE | EN ISO 13937-3 | 294,1 N | 90 N |
| DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA | prEN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N | 2,2 mm | 2,1 mm |
| OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALL'ABRASIONE | DIN EN ISO 12947-1 DIN EN ISO 12947-2 | 39.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI | |
| PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING | EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI | 4-5 | |
| OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE | EN ISO 105-B02 | 5 | |
| OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORI ALL' ABRASIONE | EN ISO 105-X12 | SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO | MOKRO/WET/ MOKRO/NASS/ UMIDO |
| | | 4-5 | 4-5 |
| VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLERANTI AZOICI | § 64 LFGB 82.02-4 | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE | |
| VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLERANTI ALLERGENICI | | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE | |
| TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO | BS 5852 Part 1 Ignition source 0 | PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO | |

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
DIFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILE

COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE
FARBNIANSEN SIND MOEGLICH

