

LIMBY

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		53% POLIESTER, 39% AKRIL, 8% LAN 53% POLYESTER, 39% ACRYLIC, 8% LINEN 53% POLIESTERSKO VLAKNO, 39% AKRILNO VLAKNO, 8% LAN 53% POLYESTER, 39% ACRYL, 8% LEINEN 53 % POLIESTERE, 39% ACRYLICA, 8% LINO	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	453 gr/m2 ±5%

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2687N	744 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	90,2 N	272,0 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	prEN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	1,2 mm	1,0 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	92.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORI ALL' ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/ UMIDO
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLERANTI AZOICI	§ 64 LFGB 82.02-4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFEE CONTENUTO DI COLERANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Part 1 Ignition source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
MOGUČA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
DIFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILE

COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE
FARBNIANSEN SIND MOEGLICH

