

RASQAR RUGANA RATINA

RASQAR

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		54% POLIESTER, 46% POLIPROPILEN 54% POLYESTER, 46% POLYPROPYLENE 54% POLIESTERSKO VLAKNO, 46% POLIPROPILENSKO VLAKNO 54% POLYESTER, 46% POLYPROPYLEN 54% POLIESTERE, 46% POLYPROPYLEN	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	319 gr/m ²
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS / RISULTATO	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	prEN ISO 13936-2 PRI/AT/KOD/BEI 180 N	4,7 mm	3,5 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	30.000 OBRATOV/REVS./OBRTAJA /TOUREN / GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4	

RUGANA

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONI		55% POLIESTER, 45% POLIPROPILEN 55% POLYESTER, 45% POLYPROPYLENE 55% POLIESTERSKO VLAKNO, 45% POLIPROPILENSKO VLAKNO 55% POLYESTER, 45% POLYPROPYLEN 55% POLIESTERE, 45% POLYPROPYLEN	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	313 gr/m ²
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS / RISULTATO	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	prEN ISO 13936-2 PRI/AT/KOD/BEI 180 N	3,7 mm	3,1 mm

OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	40.000 OBRATOV/REVS./OBRTAJA /TOUREN / GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN / GIRI	4

RATINA

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		55% POLIESTER, 45% POLIPROPILEN 55% POLYESTER, 45% POLYPROPYLENE 55% POLIESTERSKO VLAKNO, 45% POLIPROPILENSKO VLAKNO 55% POLYESTER, 45% POLYPROPYLEN 55% POLIESTERE, 45% POLYPROPYLEN	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	306 gr/m2
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS / RISULTATO	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	prEN ISO 13936-2 PRI/AT/KOD/BEI 180 N	3,2 mm	3,7 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	37.000 OBRATOV/REVS./OBRTAJA /TOUREN / GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESITENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN / GIRI	4	

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGLICH
TRA I LOTTI DI TINTURA POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

