

S A N D

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		100% POLIESTER / 78% POLESTER, 22% BOMBAŽ 100% POLYESTER / 78% POLYESTER, 22% COTTON 100% POLIESTERSKO VLAKNO / 78% POLIESTERSKO VLAKNO, 22% PAMUK 100% POLYESTER / 78% POLYESTER, 22% BAUMWOLLE 100% POLIESTERE / 78% POLIESTERE, 22% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	275 gr/m2 +/-5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS / RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
PRETRŽNI RAZTEZEK ELONGATION PRETRŽNA RASTEZLJIVOST AUSDEHNUNG CONSISTENZA TESO-ELASTICA	ISO 5081	19 %	24 %
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	ISO 5081	1442 N / 5cm	1224 N / 5cm
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	BS 3320	2 mm	1,7 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-2	60.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	ISO 12947-2	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT SOLIDITA DEL COLORE ALLA LUCE	EN 20105-B02	4-5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT SOLIDITA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		5	4
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI AZO-COLORANTI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR IMPERCETTIBILE	
VSEBNOST BARVIL, KI POVZROČAJU ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE COLORANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR IMPERCETTIBILE	

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

CIGARETNI TEST: CIGARETNI TEST: CIGARET TEST: ZIGARETTEN TEST: IGNIFUGO	BS 5852 PART 1 Ignition source 0	PRESTAL TEST PROŠAO TEST PASSED UEBERSTANDEN PASSATO
ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROPEPELENTE	

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUČA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGlich
TRA I VARI LOTTI POSSONO VERIFIARSI DELLE VARIAZIONE NEL COLORE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si