


Art. LEONARDO

SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		77% PVC, 20% POLIESTER, 3% POLIURETAN 77% PVC, 20% POLYESTER, 3% POLYURETHANE 77% PVC, 20% POLIESTER, 3% POLIURETAN 77% PVC, 20% POLYESTER, 3% POLYURETHAN 77% PVC, 20% POLIESTERE, 3% POLIURETANICA	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	500 g/m ² +/-5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
PRETRŽNI RAZTEZEK TENSILE STRENGTH PRETRŽNA RASTEZLJIVOST AUSDEHNUNG RESISTENZA ALLA TRAZIONE	DIN EN ISO 1421 Method 1	315 N	321 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	DIN EN ISO 4674-1 Method A	84,9 N	80,0 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE/POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	DIN EN ISO 13936-2 180 N Load	2,3 mm	2,0 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	Coating breakage: >100.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
	DIN EN ISO 5470-2 Method 1, Crossbred	102.400: Grade 1 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	DIN EN ISO 105-B02 Process 3	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRAZIONE	DIN EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		5	5
OBSTOJNOST NA UPOGIBANJE FLEXING ENDURANCE OTPORNOST NA SAVLIJANJE BIEGEFESTIGKEIT RESISTENZA ALLE FLESSIONI	Acc. to DIN EN ISO 321000 DIN 53359 100.000 Cycles	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	DIN EN 1021-1 -without soaking- BS 5852 Source 0 -without soaking-	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
			

MED BARVNIMI PARTIJAMI SO MOŽNA ODPORANJA V BARVI.
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE.
MOGUČA SU ODPORANJA U BOJI KOD PROIZVODNJE.
FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH.
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.