

## BIANCA QC

SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV TKANINE ZUSAMMENSETZUNG COMPOSIZIONE TESSUTO		54% POLIESTER, 42% AKRIL, 4% VISKOZA 54% POLYESTER, 42% ACRYLIC, 4% VISCOSE 54% POLIESTER, 42% AKRIL, 4% VISKOZA 54% POLYESTER, 42% ACRYL, 4% VISKOSE 54% POLIESTERE, 42% ACRILICA, 4% VISCOSA	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	<b>141 cm +/-2%</b>	TEŽA WEIGHT TEŽINA GEWICHT PESO	<b>419 gr/m<sup>2</sup> +/-5%</b>
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1800 N	1200 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	130 N	81 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	5 mm	4 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTÄNDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-1 EN ISO 12947-2	60.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/ REVS./OBRTAJA /SCHEUERTOUR EN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02 Method 2	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS5852 Source 0	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO	
ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	<b>QUICK CLEAN</b>		

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI.  
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE.  
MOGUČA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE.  
FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH.  
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

**OEKO-TEX®**  
CONFIDENCE IN TEXTILES  
**STANDARD 100**   
SP015 164683 OETI

