

MONTREAL WR

SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV TKANINE ZUSAMMENSETZUNG COMPOSIZIONE TESSUTO		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	510 g/m ² +/-5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2315 N (52,1%)	900 N (19,6%)
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREIBFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	193,6 N	106 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	1,5 mm	2,5 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-1 EN ISO 12947-2	60.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OB RTAJA /SCHEUERTOUREN/G IRI	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02	4-5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/UMI DO
		5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS

fabrics and leathers

FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	DIN EN 1021-1 -without soaking- BS 5852 Source 0 -without soaking-	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROPEPELENTE	

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI //

COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE //

MOGUĆA SU ODSSTOPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH //

TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE

