

Art. EBENE, IVOIRE, JOLIE, MACHIN, PROMESE

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		90% BOMBAŽ, 10% POLIESTER 90% COTTON, 10% POLYESTER 90% PAMUK, 10% POLIESTER 90% BAUMWOLLE, 10% POLYESTER 90% COTONE, 10% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	280 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	220 g/m ² ±5%
KRČENJE PRI PRANJU 40°C SHRINKAGE AT WASHING 40°C SAKUPLJANJE KOD PRANJA 40°C EINLAUFWERTE BEIM WASCHHE: 40°C RESTRINGIMENTO AL LAVAGGIO 40°C		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
		7%	3%



Art. STEEL, TYRES

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		59% POLIESTER, 41% BOMBAŽ 59% POLYESTER, 41% COTTON 59% POLIESTER, 41% PAMUK 59% POLYESTER, 41% BAUMWOLLE 59% POLIESTERE, 41% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	280 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	250 g/m ² ±5%
KRČENJE PRI PRANJU 40°C SHRINKAGE AT WASHING 40°C SAKUPLJANJE KOD PRANJA 40°C EINLAUFWERTE BEIM WASCHHE: 40°C RESTRINGIMENTO AL LAVAGGIO 40°C		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
		3%	4%



Art. NOVA 101

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		85% BOMBAŽ, 15% POLIESTER 85% COTTON, 15% POLYESTER 85% PAMUK, 15% POLIESTER 85% BAUMWOLLE, 15% POLYESTER 85% COTONE, 15% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	280 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	190 g/m ² ±5%
KRČENJE PRI PRANJU 40°C SHRINKAGE AT WASHING 40°C SAKUPLJANJE KOD PRANJA 40°C EINLAUFWERTE BEIM WASCHHE 40°C RESTRINGIMENTO AL LAVAGGIO 40°C		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
		7%	3%



Art. NOVA 45

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% BOMBAŽ 100% COTTON 100% PAMUK 100% BAUMWOLLE 100% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	280 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	190 g/m ² ±5%
KRČENJE PRI PRANJU 40°C SHRINKAGE AT WASHING 40°C SAKUPLJANJE KOD PRANJA 40°C EINLAUFWERTE BEIM WASCHHE 40°C RESTRINGIMENTO AL LAVAGGIO 40°C		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
		7%	3%



SUŠITI V SENCI. / DRY IN THE SHADE. / SUŠITI V HLADU. / TROCKNEN IN SCHATTEN. / ASCIUGARE ALL'OMBRA.

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI. / COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE. /
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE. / FARBNIANSEN SIND MOEGLICH. / TRA I VARI LOTTI POSSONO VERIFICARSI DELLE
VARIAZIONI NEL COLORE.