

# MERCIS

fabrics and leathers

## MEDIA QC



SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		85% POLIESTER, 15% BOMBAŽ 85% POLYESTER, 15% COTTON 85% POLIESTER, 15%, PAMUK 85% POLYESTER, 15% BAUMWOLLE 85% POLIESTERE, 15% COTONE	
ŠIRINA // WIDTH // ŠIRINA // BREITE // ALTEZZA	140 cm ±2%	TEŽA // WEIGHT // TEŽINA // GEWICHT // PESO	472 g/m <sup>2</sup> ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	
		VOTEK/WEFT/ POTKA/SCHUSS / TRAMA	
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2000 N	750 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	53 N	83 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	4 mm	3 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	80.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	6	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		4-5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	DIN 54231:2005	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
VERTIKALNI RAPORT VERTICAL REPEAT VERTIKALNI RAPORT VERTIKALRAPPORT RAPPORTO VERTICALE	34 cm	HORIZONTALNI RAPORT HORIZONTAL REPEAT HORIZONTALNI RAPORT HORIZONTALRAPPORT RAPPORTO ORRIZONTALE	35 cm
MED BARVNIMI PARTIJAMI SO MOŽNA ODSTOPANJA V BARVI // COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSTUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			

