

Sestava Composition Sirovinski sastav Zusammensetzung Composizione	70% reciklirana volna, 30% poliamid 70% recycled wool, 30% polyamide 70% reciklirana vuna, 30% poliamid 70% reciklirana Wolle, 30% Polyamid 70% lana riciclata, 30% poliammide
--	--

Širina Width Širina Breite Altezza	150 cm ±2%	Teža Weight Težina Gewicht Peso	400 g/m² ±5%
---	------------	--	--------------

Test	Standard	Rezultati Results Rezultati Ergebnis Risultati	
		Osnova Warp Osnova Kette Ordito	Votek Weft Potka Schuss Trama
Raztezna trdnost Tensile strength Čvrstoća na rastezanje Zugfestigkeit Resistenza alla trazione	EN ISO 13934-1	474 N	437 N
Raztržna trdnost Tear growth strength Čvrstoća na kidanje Weiterreissfestigkeit Resistenza alla lacerazione	EN ISO 13937-3	30,2 N	31,3 N
Drsnost niti Resistance to seam slippage Otpornost na pomjeranje / pomeranje šava Nahtschiebewiderstand Resistenza allo scorrimento della cucitura	EN ISO 13936-2	2,8 mm	2,8 mm
Piling Pilling resistance Piling Pillbildung Resistenza al pilling	EN ISO 12945-2	3-4 @ 2.000 Obratov Revs. Obrtaja Touren Giri	
Obstojnost tkanine na drgnjenje Abrasion resistance Postojanost tkanine na trljanje Scheuerbeständigkeit Resistenza all'abrasione	EN ISO 12947-1 EN ISO 12947-2	>100.000 Obratov Revs. Obrtaja Touren Giri	
Obstojnost barve na drgnjenje Colour fastness to rubbing Postojanost boje na trljanje Reibechtheit Resistenza del colore all'abrasione	EN ISO 105-X12	Suho Dry Suho Trocken Secco	Mokro Wet Mokro Nass Umido
		5	5
Obstojnost barve na svetlobo Colour fastness to light Postojanost boje na svjetlo / svetlost Lichtechtheit Resistenza del colore alla luce	EN ISO 105-B02	>5	
Vsebnost azo barvil in alergenih barvil Content of azo dyes and allergenic dyes Sadržaj azo boja i alergijskih boja Azofarbstoffe und allergene Farbstoffe Contenuto di coloranti azoici e allergenici	DIN EN 14362-1 DIN EN 14362-3 DIN 54231	Ni zaznana Not detectable Ne sadrži Nicht nachweisbar Non rilevabile	
Vsebnost formaldehida Formaldehyde content Sadržaj formaldehida Formaldehydgehalt Contenuto di formaldeide	EN ISO 14184-1	Ni zaznana Not detectable Ne sadrži Nicht nachweisbar Non rilevabile	

Info	
Test negorljivosti Fire retardant Test negorivosti Brennverhalten Ignifugo	DIN EN 1021-1 without soaking DIN EN 1021-2 without soaking BS 5852 Source 0 without soaking BS 5852 Source 1 without soaking UNI 9175-2010 classe 1.IM

Vzdrževanje Maintenance Održavanje Wartung Manutenzione	    
--	--



We are GRS certified, CUC 1127829.
Only the products which are covered by a
valid transaction certificate are GRS certified.