


AFRICA SNAKE / CHEETAH / FISH / GEPARD / GIRAFFE / JAGUAR / OSTRICH / SKIN / TIGER / ZEBRA (printed on Bora) WATER REPELLENT

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	330 g/m ² ±5%
TEST	STANDARD	REZULTAT / RESULTS / REZULTAT / ERGENIS / RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	DIN EN ISO 13934-1	495 N	486 N
RAZTRŽNA TRDNOST TEAR GROWTH RESISTANCE ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	DIN EN ISO 13937-3	86 N	97 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE/POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SPOSTAMENTO DELLA CUCITURA	DIN EN ISO 13936-2 PRIŽAT/KOD/BEI /A 180 N	2,3 mm	3 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	>30.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	DIN EN ISO 12945-2	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT FOTOSTABILITÀ	DIN EN ISO 105-B02 Process 3, Exposure level 5	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA ALL'ATTRITO	DIN EN ISO 105-X12	SUHO/DRY/SUHO/SUVO /TROCKEN/SECCO	MOKRO/WET/MOKRO/ NASS/UMIDO
		5	5
AZO BARVILA AZO DYES AZO BOJE AZOFARBSTOFFE COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
ALERGENA IN KANCENOGENA BARVILA ALLERGENIC AND CARCINOGENIC DYES ALERGENA I KANCEROGENA BOJILA DISPERSIONSFARBSTOFFE, BESTIMMUNG ALLERGISIERENDER UND KANZEROGENER FARBSTOFFE COLORANTI ALLERGIZZANTI E CANCEROGENI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FREIER FORMALDEHYD FORMALDEIDE	DIN EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI IGNITABILITY TEST NEGORIVOSTI ENTZÜNDBARKEIT VERIFICA DELL'ACCENDIBILITÀ	DIN EN 1021-1 -without soaking- BS 5852 Source 0 -without soaking-	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI. COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE. MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE. FARBNIANSEN SIND MOEGLICH. TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.			

Raport / Repeat / Rapport / Rapporto	↔	↕
AFRICA SNAKE	50 cm	50 cm
AFRICA CHEETAH	25 cm	25 cm
AFRICA FISH	8 cm	8 cm
AFRICA GEPARD	45 cm	45 cm
AFRICA GIRAFFE	40 cm	40 cm
AFRICA JAGUAR	25 cm	25 cm
AFRICA OSTRICH	15 cm	15 cm
AFRICA TIGER	60 cm	70 cm
AFRICA ZEBRA	35 cm	35 cm