


**DEER FOREST / JOHN /**

**JUMP / LAND / PINE / TROPHY (printed on Bora P)**

**WATER REPELLENT**

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	330 g/m <sup>2</sup> ±5%
TEST		STANDARD	REZULTAT / RESULTS / REZULTAT / ERGENIS / RISULTATI
			OSNOVA / WARP / OSNOVA / KETTE / ORDITO
			VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE		DIN EN ISO 13934-1	495 N
RAZTRŽNA TRDNOST TEAR GROWTH RESISTANCE ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE		DIN EN ISO 13937-3	86 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE/POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SPOSTAMENTO DELLA CUCITURA		DIN EN ISO 13936-2 PRI/AT/KOD/BEI /A 180 N	2,3 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE		DIN EN ISO 12947-1 DIN EN ISO 12947-2	>100.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING		DIN EN ISO 12945-2	5
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT FOTOSTABILITÀ		DIN EN ISO 105-B02 Process 3, Exposure level 5	5
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA ALL'ATTRITO		DIN EN ISO 105-X12	SUHO/DRY/SUHO/SUVO /TROCKEN/SECCO
			MOKRO/WET/MOKRO/ NASS/UMIDO
			5
AZO BARVILA AZO DYES AZO BOJE AZOFARBSTOFFE COLORANTI AZOICI		DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
ALERGENA IN KANCENOGENA BARVILA ALLERGENIC AND CARCINOGENIC DYES ALERGENA I KANCEROGENA BOJILA DISPERSIONSFARBSTOFFE, BESTIMMUNG ALLERGISIERENDER UND KANZEROGENER FARBSTOFFE COLORANTI ALLERGIZZANTI E CANCEROGENI		DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
FORMALDEHID FORMALDEHYDE FORMALDEHID FREIER FORMALDEHYD FORMALDEIDE		DIN EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
TEST NEGORLJIVOSTI IGNITABILITY TEST NEGORIVOSTI ENTZÜNDBARKEIT VERIFICA DELL'ACCENDIBILITÀ		DIN EN 1021-1 -without soaking-  BS 5852 Source 0 -without soaking-	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTOPANJA V BARVI. COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE. MOGUĆA SU ODPSTUPANJA U BOJI KOD PROIZVODNJE. FARBNIANSEN SIND MOEGLICH. TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.			

<b>Raport / Repeat / Rapport / Rapporto</b>	<b>↔</b>	<b>↕</b>
<b>DEER FOREST</b>	<b>46,5 cm</b>	<b>46,5 cm</b>
<b>DEER JOHN</b>	<b>48 cm</b>	<b>50 cm</b>
<b>DEER JUMP</b>	<b>48 cm</b>	<b>50 cm</b>
<b>DEER LAND</b>	<b>80 cm</b>	<b>80 cm</b>
<b>DEER PINE</b>	<b>48 cm</b>	<b>50 cm</b>
<b>DEER TROPHY</b>	<b>20 cm</b>	<b>20 cm</b>