

## LYRA

## WATER REPELLENT

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	100% POLIESTER 100 %POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	570 g/m <sup>2</sup> ±5%

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2789 N	1722 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	390 N	272 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2,8 mm	3,7 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-1 EN ISO 12947-2	>100.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 5.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	DIN EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 source 0 DIN EN 1021-1 without soaking	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	

# MERCIS

fabrics and leathers

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI  
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE  
MOGUČA SU ODSUPANJA U BOJI KOD PROIZVODNJE  
FARBNIANSEN SIND MOEGLICH  
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

