



## BROOKLYN DIAMOND

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		51% PVC, 15% POLIESTER, 34% PU 51% PVC, 15% POLYESTER, 34% PU 51% PVC, 15% POLIESTER, 34% PU 51% PVC, 15% POLYESTER, 34% PU 51% PVC, 15% POLIESTERE, 34% PU	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	135 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	1000 g/m <sup>2</sup> +/-5%
TEST	STANDARD	REZULTAT/ RESULT/ REZULTAT/ ERGEBNIS/ RISULTATO	
		OSNOVA/WARP/OSNOVA/ KETTE/ORDITO	VOTEK/WEFT/POTKA/ SCHUSS/TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	DIN EN ISO 13934-1	676 N	561 N
RAZTRŽNA TRDNOST TEAR GROWTH RESISTANCE ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	DIN EN ISO 13937-3	78,4 N	61,3 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	DIN EN ISO 13936-2 PRI/ AT/ KOD/ BEI/ A 180 N	2 mm	2 mm
PREPOGIBNOST PERMANENT CREASING BEHAVIOUR OTPORNOST NA SAVIJANJE DAUERBIEGEFESTIGKEIT REAZIONE ALLA PIEGA CONTINUA	DIN EN ISO 5402-1 100 000 cycles	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	DIN EN ISO 12947-1  DIN EN ISO 12947-2	BROOKLYN QUILTED FACE: > 100.000 OBRATOV/CYCLES./OBRTAJA/TOUREN/GIRI  MEXICO QUILTED SEAM: 12.000 OBRATOV/CYCLES./OBRTAJA/TOUREN/GIRI	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	DIN EN ISO 105-B02 Process 3, Exposure level 5	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	DIN EN ISO 105-X12	SUHO/ DRY/ SUVO/ TROCKEN/SECCO	MOKRO/ WET/ MOKRO/ NASS/UMIDO
		4-5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

# MERCIS

fabrics and leathers

FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	DIN EN ISO 14184-1	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 -without soaking-  DIN EN 1021-1 -without soaking-	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO
UPORABA / APPLICATION / UPOTREBA / VERWENDUNG / USO		
 		

ČIŠČENJE / CLEANING / ČIŠČENJE / PFLEGE UND REINIGUNG / MANUTENZIONE E PULIZIA

