

SANTOS

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% poliester 100% polyester 100% poliestersko vlakno 100% polyester 100% poliestere	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	270 gr/m2

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATO	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	ISO 12945-2	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA COLORE ALLA LUCE	ISO 05-B02 (up to 150 hrs)	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALLA ABRASIONE	ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		4-5	4-5
OBSTOJNOST BARVE NA VODO COLOUR FASTNESS TO WATER POSTOJANOST BOJE NA VODU WASSERECHTHEIT RESISTENZA COLORE ALL'ACQUA	ISO 105-E01	5	
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS / RISULTATO	
NEGORLJIVOST FIRE RETARDANT NEGORIVOST BRENNVERHALTEN IGNIFUGO	IMO A652-16 BS 5852 CRIB 5 EN 1021 – 1&2	PRESTAL/PASS/PROŠAO/ÜBERSTANDEN/ SUPERATO	

MED BARVNIMI PARTIJAMI SO MOŽNA ODPANJA V BARVI
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUĆA SU ODPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGLICH
DIFFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILI

