

## KYOTO

|  |        |   |           |
|--|--------|---|-----------|
| SESTAVA<br>COMPOSITION<br>SIROVINSKI SASTAV<br>ZUSAMMENSETZUNG<br>COMPOSIZIONE |        | 100% poliester<br>100% polyester<br>100% poliester<br>100% polyester<br>100% poliestere |           |
| ŠIRINA<br>WIDTH<br>ŠIRINA<br>BREITE<br>ALTEZZA                                 | 140 cm | TEŽA<br>WEIGHT<br>TEŽINA<br>GEWICHT<br>PESO   | 528 gr/m2 |

| TEST   | STANDARD   | REZULTAT/RESULTS/REZULTAT/ERGEBNIS /<br>RISULTATO |   |
|--|--|---|---|
|  |  | OSNOVA/WARP/<br>OSNOVA/KETTE /<br>ORDITO          | VOTEK/WEFT/<br>POTKA/SCHUSS /<br>TRAMA  |
| RAZTEZNA TRDNOST<br>TENSILE STRENGTH<br>ČVRSTOČA NA RASTEZANJE<br>ZUGFESTIGKEIT<br>RESISTENZA ALLA TRAZIONE  | ISO 13934-1  | 640 N   | 710 N                                   |
| DRSNOST NITI<br>RESISTANCE TO SEAM SLIPPAGE<br>OTPORNOST NA POMJERANJE /POMERANJE ŠAVA<br>NAHTSCHIEBEWIDERSTAND<br>RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA                      | ISO 13936-2  | 4,7 mm  | 4,7 mm                                  |
| OBSTOJNOST BARVE NA DRGNJENJE<br>COLOUR FASTNESS TO RUBBING<br>POSTOJANOST BOJE NA TRLJANJE<br>REIBECHTHEIT<br>RESISTENZA COLORE ALLA ABRASIONE                                    | ISO 105-X12  | SUHO/DRY/<br>SUHO/TROCKEN /<br>SECCO<br>4-5       | MOKRO/WET/<br>MOKRO/NASS / UMIDO<br>4-5 |
| OBSTOJNOST TKANINE NA DRGNJENJE<br>ABRASION RESISTANCE<br>POSTOJANOST TKANINE NA TRLJANJE<br>SCHEUERBESTAENDIGKEIT<br>RESISTENZA TESSUTO ALLA ABRASIONE                            | ISO 12947-1-2 MOD.BS 2543  | 55.000<br>OBRATOV/CYCLES./OBRTAJA /TOUREN/GIRI    |   |
| PILING<br>PILLING RESISTANCE<br>PILING<br>PILLBILDUNG<br>RESISTENZA PILLING  | ISO 12945-2  | 5   |   |
| OBSTOJNOST BARVE NA UMETNO SVETLOBO<br>COLOUR FASTNESS TO ARTIFICIAL LIGHT<br>POSTOJANOST BOJE NA UMJETNO SVJETLO<br>KUNSTLICHTECHTHEIT<br>RESISTENZA COLORE ALLA LUCE ARTIFICIALE | ISO 105-B02  | 7   |   |
| TEST   | STANDARD   | REZULTAT/RESULTS/REZULTAT/ERGEBNIS/RISUL<br>TATO  |   |
| NEGORLJIVOST<br>FIRE RETARDANT<br>NEGORIVOST<br>BRENNVERHALTEN<br>IGNIFUGO   | EN 1021-1&2<br>BS 5852 source 1+2<br>BS 5852 CRIB 5<br>IMO A652-16 | PRESTAL/PASS/PROŠAO/ÜBERSTANDEN/<br>SUPERATO      |   |

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI  
COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE  
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE  
FARBNIANSEN SIND MOEGLICH  
DIFFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILI.

