

PEGASUS QC

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	66% RECIKLIRAN POLIESTER, 20% POLIESTER, 8% ORGANSKI BOMBAŽ, 6% BOMBAŽ 66% RECYCLED POLYESTER, 20% POLIESTER, 8% ORGANIC COTTON, 6% COTTON 66% RECIKLIRANI POLIESTER, 20% POLIESTER, 8% ORGANSKI PAMUK, 6% PAMUK 66% RECYCLER POLYESTER, 20% POLYESTER, 8% ORGANISCHE BAUMWOLLE, 6% BAUMWOLLE 66% POLIESTERE RICICLATO, 20% POLIESTERE, 8% COTONE ORGANICO, 6% COTONE		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	144 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	445 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1900 N	1500 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	240 N	300 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	35.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	8	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
VERTIKALNI RAPORT VERTICAL REPEAT VERTIKALNI RAPORT VERTIKALRAPPORT RAPPORTO VERTICALE	↕	56,5 cm	
HORIZONTALNI RAPORT HORIZONTAL REPEAT HORIZONTALNI RAPORT HORIZONTALRAPPORT RAPPORTO ORIZZONTALE	↔	18 cm	
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			

