

LEON

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		40% POLIESTER, 31% AKRIL, 28% BOMBAŽ, 1 % POLIAMID 40% POLYESTER, 31% ACRYLIC, 28% COTTON, 1% POLYAMIDE 40% POLIESTER, 31% AKRIL, 28% PAMUK, 1% POLIAMID 40% POLYESTER, 31% ACRYL, 28% BAUMWOLLE, 1% POLYAMID 40% POLIESTERE, 31% ACRILICA, 28% COTONE, 1% POLIAMMIDE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	515 g/m² ±5%

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2030 N	453 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	174 N	45 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2,5 mm	1,9 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-1 EN ISO 12947-2	80.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	2000 OBRATOV / REVS./ OBRATAJA /TOUREN / GIRI 4 – 5	5000 OBRATOV / REVS./ OBRATAJA /TOUREN / GIRI 4
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO 5	MOKRO/WET/ MOKRO/NASS / UMIDO 5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI	DIN EN 14362-1 / -3 § 64 LFGB B 82.02-2 / -15	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	ISO 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS

fabrics and leathers

TEST NEGORLJIVOSTI: FIRE RETARDANT: TEST NEGORIVOSTI: BRENNVERHALTEN: IGNIFUGO:	BS 5852 Source 0 DIN EN 1021-1	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
---	-----------------------------------	---

ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	QUICK CLEAN QUICK CLEAN QUICK CLEAN QUICK CLEAN QUICK CLEAN
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE MOGUČA SU ODSSTUPANJA U BOJI KOD PROIZVODNJE FARBNIANSEN SIND MOEGLICH TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.	



LIKANJE NA HRBTNI STRANI // IRON ON REVERSE SIDE // PEGLANJE NA NALIČJU/POLEDJINI // AUF DER RÜCKSEITE BÜGELN // STIRATURA SUL ROVESCIO

	OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
SPREMEMBE DIMENZIJ PRI PRANJU NA 30°C DIMENSIONAL CHANGE FOR WASHING 30°C PROMJENE DIMENZIJA KOD PRANJA NA 30°C MÄÄNDERUNG NACH WÄSCHE BEI 30°C ALTERAZIONE DIMENSIONALE PER LAVAGGIO A 30°C	-3 %	- 3 %
SPREMEMBE DIMENZIJ PRI KEMIČNEM ČIŠČENJU DIMENSIONAL CHANGE FOR DRY CLEANING PROMJENE DIMENZIJA KOD KEMIJSKOG ČIŠČENJA MÄÄNDERUNG NACH CHEMISCHER REINIGUNG ALTERAZIONE DIMENSIONALE PER LAVAGGIO A SECCO	-1,2 %	-1 %