

UMBRIA

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	TEFLON	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	320 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	240 g/m ²	
TEST		STANDARD	REZULTAT/RESULTS/REZULTAT/ ERGENIS/ RISULTATI	
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALLA ABRASIONE		DIN EN ISO 12947-2	20.000 OBRATOV/REVS./OBRTAJA /TOUREN / GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING		ISO 12945-2 (1 - 5)	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESITENZA COLORE ALLA LUCE		EN ISO 105-B02 (1 - 8)	4-5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALLA ABRASIONE		EN ISO 105-X12 (1 - 5)	5	
OBSTOJNOST BARVE NA PRANJE 60°C COLOURFASTNESS TO WASHING 60°C POSTOJANOST BOJE NA PRANJE 60°C FARBECHTHEIT - WASCHEN 60°C RESISTENZA COLORE AL LAVAGGIO 60°C		EN ISO 105-C06 (1 - 5)	5	
KRČENJE SHRINKAGE SKUPLJANJE EINLAUFWERT RESTRINGIMENTO		PO OSNOVI WARP PO OSNOVI KETTE ORDITO	2%	
		PO VOTKU WEFT PO POTCI SCHUSS TRAMA	1%	

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTOPANJA
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUĆA SU ODPSTUPANJA U BOJI
FARBNIANSEN SIND MOEGLICH
DIFFERENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILI

