

OVIEDO

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	360 g/m ² ±5%
TEST	STANDARD	REZULTAT / RESULTS / REZULTAT / ERGEBNIS / RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1463 N	1104 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE / POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	1,4 mm	1,5 mm
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	88,5 N	45,5 N
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	2000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI	5000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
		4 - 5	4 - 5
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALL'ABRASIONE	EN ISO 12947-1/-2	>100.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02 Exposure level 7	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT SOLIDITÀ DEL COLORE ALLO SFREGAMENTO	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4 - 5	4 - 5
AZO BARVILA AZO DYES AZO BOJE AZOFARBSTOFFE COLORANTI AZOICI	DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
ALERGENA IN KANCENOGENA BARVILA ALLERGENIC AND CARCINOGENIC DYES ALERGENA I KANCEROGENA BOJILA ALLERGISIERENDE UND KANZEROGENE FARBSTOFFE COLORANTI ALLERGIZZANTI E CANCEROGENI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FREIER FORMALDEHYD FORMALDEIDE	DIN EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 source 0 DIN EN 1021-1	PRESTAL TEST PASSED PROŠAO TEST UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO	QUICK CLEAN		

MERCIS

fabrics and leathers

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI. // COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE. //
MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE. // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH. //
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

