

IMPRESS



IN-OUT
DOOR



WATER
REPELLENT



QUICK
CLEAN



RE-FAB
RECYCLED FABRICS

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		93% RECIKLIRAN POLIOLEFIN, 7% POLIESTER 93% SOLUTION DYED RECYCLED POLYOLEFIN, 7% POLYESTER 93% RECIKLIRANI POLIOLEFIN, 7% POLIESTER 93% REZYKLIERTES POLYOLEFIN, 7% POLYESTER 93% POLIOLEFINE RICICLATO, 7% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	138 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	472 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI OSNOVA / WARP / OSNOVA / KETTE / ORDITO VOTEK / WEFT / POTKA / SCHUSS / TRAMA	
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1600 N	1000 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	224 N	160 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	40.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	8	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 CAL 117/SE NFPA 260 Class 1 (UFAC) MVSS 302	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			



Po potrebi je možno pranje do 60°C
If necessary, washing up to 60°C is possible
Po potrebi je moguće pranje do 60°C
Bei Bedarf ist Waschen bis zu 60°C möglich
Se necessario, è possibile lavare fino a 60°C



STANDARD
100
SP015 248657
OETI



We are GRS certified, CUC 1127829.
Only the products which are covered by a
valid transaction certificate are GRS certified.