

## SHEEN



SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		100% RECIKLIRAN POLIOLEFIN 100% SOLUTION DYED RECYCLED POLYOLEFIN 100% RECIKLIRANI POLIOLEFIN 100% REZYKLIERTES POLYOLEFIN 100% POLIOLEFINE RICICLATO	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	349 g/m <sup>2</sup> ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1500 N	1700 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	124 N	120 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
RAPORT REPEAT RAPORT RAPPORT RAPPORTO		↕ 2,2 cm	↔ 1,5 cm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	50.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	8	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 CAL 117/SE NFPA 260 Class 1 (UFAC) MVSS 302	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
MED BARVNIMI PARTIJAMI SO MOŽNA ODSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			



Po potrebi je možno pranje do 60°C  
If necessary, washing up to 60°C is possible  
Po potrebi je moguće pranje do 60°C  
Bei Bedarf ist Waschen bis zu 60°C möglich  
Se necessario, è possibile lavare fino a 60°C



STANDARD  
100  
SP015 248657  
OETI



We are GRS certified, CUC 1127829.  
Only the products which are covered by a  
valid transaction certificate are GRS certified.