

EARTHWILD

QUICK
CLEANRE-FAB
RECYCLED FABRICS

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		65% RECIKLIRAN POLIESTER, 32% EKO-BOMBAŽ, 3% LAN 65% RECYCLED POLYESTER, 32% ORGANIC COTTON, 3% LINEN 65% RECIKLIRAN POLIESTER, 32% BIO- PAMUK, 3% LAN 65% REZYKLIERTES POLYESTER, 32% BIO- BAUMWOLLE, 3% LEINEN 65% POLIESTERE RICICLATO, 32% COTONE BIOLOGICO, 3% LINO	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	142 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	520 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	890 N	970 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	160 N	310 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	40.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRATAJA /SCHEUERTOUREN/GIRI	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		5	5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 EN 1021 part 1	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO	QUICK CLEAN		
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI // COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			

STANDARD
100
SP015 248657
OETIWe are GRS certified, CUC 1127829.
Only the products which are covered by a
valid transaction certificate are GRS certified.