

BILBAO



SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLIESTER 100% POLIESTERE		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	143 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	505 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1600 N	1100 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	96 N	110 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	50.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
BARVNA OBSTOJNOST PRI UPORABI COLOUR FASTNESS TO WEAR POSTOJANOST BOJE KOD UPOTREBE FARBECHEITHEIT BEI GEBRAUCH SOLIDITÀ DEL COLORE ALL'USURA	EN ISO 12947-2	3	PO / AFTER / NAKON / NACH / DOPO 40.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHEITHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	8	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHEITHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 EN 1021-1 CAL 117 FMVSS 302 NFPA 260	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO	WATER REPELLENT		
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			



STANDARD
100
SP015 164683
OETI