

## LINIQUE



RE-FAB  
RECYCLED FABRICS



QUICK  
CLEAN

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	40% RECIKLIRAN POLIESTER, 36% RECIKLIRAN POLIPROPILEN, 24% AKRIL 40% RECYCLED POLYESTER, 36% RECYCLED POLYPROPYLENE, 24% ACRYLIC 40% RECIKLIRAN POLIESTER, 36% RECIKLIRAN POLIPROPILEN, 24% AKRIL 40% REZYKLIERTES POLYESTER, 36% REZYKLIERTES POLYPROPYLEN, 24% ACRYL 40% POLIESTERE RICICLATO, 36% POLIPROPILENE RICICLATO, 24% ACRILICA		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	497 g/m <sup>2</sup> ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1200 N	1800 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	410 N	130 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	80.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
BARVNA OBSTOJNOST PRI UPORABI COLOUR FASTNESS TO WEAR POSTOJANOST BOJE KOD UPOTREBE FARBECHTHEIT BEI GEBRAUCH SOLIDITÀ DEL COLORE ALL'USURA	EN ISO 12947-2	4	PO / AFTER / NAKON / NACH / DOPO 80.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	6	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 CAL TB 117 NFPA 260	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			



STANDARD  
100  
SP015 248657  
OETI



www.quick-clean.info

We are GRS certified, CUC 1127829.  
Only the products which are covered by a  
valid transaction certificate are GRS certified.