




MEX

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	46% BOMBAŽ, 41% POLIESTER, 13% LAN 46% COTTON, 41% POLYESTER, 13% LINEN 46% PAMUK, 41% POLIESTER, 13% LAN 46% BAUMWOLLE, 41% POLYESTER, 13% LEINEN 46% COTONE, 41% POLIESTERE, 13% LINO		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	139 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	433 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	490 N	1000 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	150 N	37 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	100.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
BARVNA OBSTOJNOST PRI UPORABI COLOUR FASTNESS TO WEAR POSTOJANOST BOJE KOD UPOTREBE FARBECHEITHEIT BEI GEBRAUCH SOLIDITÀ DEL COLORE ALL'USURA	EN ISO 12947-2	3-4	PO / AFTER / NAKON / NACH / DOPO 100.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	3	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHEITHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 CAL 117 FMVSS 302 NFPA 260	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
KRČENJE SHRINKING SKUPLJANJE SCHRUMPFUNG RESTRINGIMENTO		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
		-3.75 %	-0.33 %
		-1.73 %	-0.53 %
		-0.40 %	-0.40 %
MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODPSTUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			



STANDARD
100
SP015 164683
OETI

