

ASSET



SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE	51 % RECIKLIRAN POLIESTER, 23 % AKRIL, 15 % VISKOZA, 7 % LAN, 4 % POLIESTER 51% RECYCLED POLYESTER, 23% ACRYLIC, 15% VISCOSE, 7% LINEN, 4% POLYESTER 51 % RECIKLIRANI POLIESTER, 23 % AKRIL, 15 % VISKOZA, 7 % LAN, 4 % POLIESTER 51 % RECYCELTES POLYESTER, 23 % ACRYL, 15 % VISKOSE, 7 % LEINEN, 4 % POLYESTER 51% POLIESTERE RICICLATO, 23% ACRILICA, 15% VISCOSA, 7% LINO, 4% POLIESTERE		
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	480 g/m ² ±5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1200 N	1600 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	220 N	130 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	2 mm	2 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	55.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
BARVNA OBSTOJNOST PRI UPORABI COLOUR FASTNESS TO WEAR POSTOJANOST BOJE KOD UPOTREBE FARBECHTHEIT BEI GEBRAUCH SOLIDITÀ DEL COLORE ALL'USURA	EN ISO 12947-2	4-5	PO / AFTER / NAKON / NACH / DOPO 55.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	4-5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
		4-5	4-5
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 Source 0 CAL TB 117 NFPA 260 FMVSS 302	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO	QUICK CLEAN		
MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTOPANJA V BARVI // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE // MOGUĆA SU ODPSTUPANJA U BOJI KOD PROIZVODNJE // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH // TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE			