

MORALES



Sestava Composition Sirovinski sastav Zusammensetzung Composizione	100% Poliester 100% Polyester 100% Poliester 100% Polyester 100% Poliestere
--	---

Širina Width Širina Breite Altezza	142 cm ±2%	Teža Weight Težina Gewicht Peso	520 g/m² ±5%
---	------------	--	--------------

Test	Standard	Rezultati Results Rezultati Ergebnis Risultati	
		Osnova Warp Osnova Kette Ordito	Votek Weft Potka Schuss Trama
Raztezna trdnost Tensile strength Čvrstoća na rastezanje Zugfestigkeit Resistenza alla trazione	EN ISO 13934-1	890 N	1100 N
Raztržna trdnost Tear growth strength Čvrstoća na kidanje Weiterreissfestigkeit Resistenza alla lacerazione	EN ISO 13937-3	230 N	140 N
Drsnost niti Resistance to seam slippage Otpornost na pomjeranje / pomeranje šava Nahtschiebewiderstand Resistenza allo scorrimento della cucitura	EN ISO 13936-2	3 mm	3 mm
Piling Pilling resistance Piling Pillbildung Resistenza al pilling	EN ISO 12945-2	3-4	
Obstojnost tkanine na drgnjenje Abrasion resistance Postojanost tkanine na trljanje Scheuerbeständigkeit Resistenza all'abrasione	EN ISO 12947-2	55.000 Obratov Revs. Obrtaja Touren Giri	
Barvna obstojnost pri uporabi Colour fastness to wear Postojanost boje kod upotrebe Farbechtheit bei Gebrauch Solidità del colore all'usura	EN ISO 12947-2	3-4 @ 20.000 Obratov Revs. Obrtaja Touren Giri	
Obstojnost barve na drgnjenje Colour fastness to rubbing Postojanost boje na trljanje Reibechtheit Resistenza del colore all'abrasione	EN ISO 105-X12	Suho Dry Suho Trocken Secco	Mokro Wet Mokro Nass Umido
		4-5	4-5
Obstojnost barve na svetlobo Colour fastness to light Postojanost boje na svjetlo / svetlost Lichtechtheit Resistenza del colore alla luce	EN ISO 105-B02	8	

Info

Test negorljivosti Fire retardant Test negorivosti Brennverhalten Ignifugo	EN 1021-1 BS 5852 Source 0 CAL TB 117 NFPA 260
---	---

Vzdrževanje Maintenance Održavanje Wartung Manutenzione	 Likanje po hrbtni strani. Ironing on the reverse side. Peglanje na poledini. Rückseite bügeln. Stirare sul retro del tessuto.
--	--



STANDARD
100
SP015 165288
OETI

